
CONICAL K-LOCK

Steel & Stainless



| CONICAL K-LOCK NUTS SAE J238 | | | | | | | | | | | | | |
|---|--------|--------------------|------|------------------|-----------------|------|----------------------|------|---|------------------------------|------|--------------------------|------|
| Nominal Size or Basic Thread Diameter | | F Across the Flats | | C Across Corners | N Nut Height | | W Washer Diameter | | T Washer Material Thick- ness | H Full Assembly Height | | R Washer Rim Width | |
| | | | | | | | | | | | | | |
| 4 | 0.1120 | .250 | .241 | .272 | .098 | .092 | .333 | .323 | .015 | .150 | .130 | .015 | .010 |
| 6 | 0.1380 | .312 | .302 | .344 | .098 | .092 | .333 | .323 | .015 | .150 | .130 | .015 | .010 |
| 8 | 0.1640 | .344 | .332 | .378 | .130 | .117 | .380 | .370 | .030 | .195 | .170 | .015 | .010 |
| 10 | 0.1900 | .376 | .362 | .410 | .130 | .117 | .408 | .395 | .020 | .195 | .170 | .015 | .010 |
| 1/4 | 0.2500 | .438 | .423 | .482 | .130 | .117 | .506 | .494 | .025 | .195 | .170 | .015 | .010 |
| • 1/4 | 0.2500 | .438 | .423 | .482 | .130 | .117 | .750 | .730 | .057 | | | | |
| 5/16 | 0.3125 | .500 | .489 | .557 | .195 | .180 | .569 | .555 | .030 | .265 | .240 | .020 | .015 |
| 3/8 | 0.3750 | .562 | .551 | .628 | .227 | .210 | .632 | .618 | .030 | .300 | .260 | .020 | .015 |
| • 3/8 | 0.3750 | .562 | .551 | .628 | .337 | .310 | 1.010 | .990 | .062 | .415 | .385 | - | - |

 $[\]bullet$ This size is not governed by the SAE J238 standard.

| Description | A hex nut pre-assembled with a free-spinning conical washer. A high tension is maintained in the screw and nut assembly as the nut is tightened against the bearing surface. | | | | | | |
|---------------------------|---|--|--|--|--|--|--|
| Applications / Advantages | Having the washer pre-assembled with the nut shortens installation time. Conical washer assemblies can compensate for joint contraction and expansion and can span slightly oversized holes. | | | | | | |
| Material | Nuts: Shall be made from a low carbon steel that conforms to the following chemical composition: **Carbon: 0.47% max.; **Phosphorous: 0.12% max.; **Sulfur: 0.15% max.** **Washers: SAE 1050 - 1065 carbon steel, fabricated and heat-treated** | | | | | | |
| Hardness | Nuts: No. 4 thru #12 diameter: No standard applies 1/4" and larger: Rockwell HRC 32 maximum | | | | | | |
| กสเนแซรร | Washers: Rockwell C 44 - 48 Rockwell C 46 - 50 (when austempering process is used) | | | | | | |
| Plating | Nuts are usually supplied with a zinc or black oxide finish. See Appendix-A for more information. | | | | | | |